

Product Description

Paraseal® GM/LG – 60 mil is a sheet waterproofing and methane-mitigating membrane consisting of 60 mils of HDPE, expandable granular bentonite and a protective layer of spun-bonded polyester. The composite weight of the sheet is up to 1.5 lb/ft², creating a dual waterproofing system. The HDPE extends beyond the bentonite on the perimeter edges to create a clean surface for extruded weld or wedge weld installation.

Basic Uses

Paraseal GM/LG – 60 mil is designed for use in post-installation submerged conditions, on blindside walls, shotcrete walls and under slab where hydrostatic water head and/or methane conditions exist. It may also be used on backfilled walls.

Features and Benefits

- The Paraseal GM/LG – 60 mil system combines the dual waterproofing system with wedge weld or extruded welded seams to create a robust yet flexible waterproof and methane-mitigating membrane.
- The nature of the Paraseal waterproofing system also allows for installation over green or damp surfaces accelerating the construction process.
- The bentonite can expand up to 8 times its original thickness to stop water that may make it past the HDPE layer, providing a second layer of protection.

Availability

Paraseal GM/LG 60-mil is available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Packaging

- 8' x 180' (2.4 M x 54.86 M) rolls
- 17.5' x 180' (5.3 M x 54.86 M) rolls

Storage

Protect from moisture. Store on a skid or pallet and cover with polyethylene or tarp. Do not double stack pallets. Prevent hydration of bentonite until the sheet is installed and under recommended compaction.

Applicable Standards

Paraseal GM/LG – 60 mil meets the City of Los Angeles (COLA) approval Standards (RR25425).

Limitations

- Paraseal products require a minimum of 24 psf of compaction/confinement in order to function as designed.
- Paraseal GM/LG - 60 mil is not to be installed over ponding or standing water or snow.
- If ground water is brackish, please contact your local Tremco Sales Representative four weeks prior to a pending application, and provide a water and/or soil sample for testing purposes in order to determine the correct bentonite formula for your project's application.
- If backfill contains substantial amounts of either lava rock, basalt or any other coarse or highly abrasive materials, a protection course or drainage mat may be required. Contact your local Tremco Sales Representative or Technical Service at 866-209-2404 for details.
- Use of Paraseal GM/LG - 20 mil in post-installation submerged conditions requires prior approval from Tremco.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

Paraseal® GM/LG - 60 mil

HDPE/Bentonite Sheet Membrane Dual Waterproofing System

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION
Color (Bentonite/HDPE)	Gray/Black
Installation Temperatures	-25 to 130 °F (-31.7 to 54.4 °C)
Freeze/Thaw Cycles	No effect before or after installation
Resistance to Chemicals & Gases	Extremely high resistance. Contact Tremco for specific information.
Life Expectancy	Indefinite

PROPERTY	TEST METHOD	VALUES US	VALUES SI
Elongation	ASTM D412 Type 4 Dumbbell	700%	
Strength at Break	ASTM D412	4,050 lb/in ²	284.74 kg/cm ²
Strength at Break	ASTM D6693, Type IV	243 lb/in	43.39 kg/cm
Resistance to Micro-organisms (bacteria, fungi, mold, yeast)	ASTM D4068	Unaffected	
Index Puncture Resistance	ASTM D4833	78.17 lb/ft	116.32 kg/M
Resistance to Hydrostatic Head Pressure	ASTM D5385	231' of H ₂ O	
Hydrostatic Resistance (with Para JT™ Tape)	ASTM D5385	>100 psi (>231 ft/H ₂ O)	(>68.9 N/cm ²) (>70.4 M/H ₂ O)
Permeance	ASTM E96	0.029 US Perms	1.7 ng/Pa·s·m ²
Puncture Resistance (load)	ASTM E154	454 lbf	2019.49 N

All data based on 60-mil HDPE

**0416/PARAGMLG20DS-BG****Tremco Commercial Sealants & Waterproofing**

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555